

Interliner

Corrugated case material for flat inner layers of corrugated board

Indicators		Norms							
Basis weight, g/m ²		42 ±1	43 ±1	45 ±1	47 ±1	48 ±1	48,8 ±1	52 ±1,5	55 ±3
Fibre mix		TMP – 100%							
Corrugated Medium Test (CMT ₃₀), N, min		25		35			45		
Absolute bursting strength, kPa, min		80		90			100		
Tensile strength in MD (machine direction), kN/m, min.		1,9		2,2			2,5		
Corrugated Crush Test (CCT ₃₀), kN/m, min.		0,20		0,25			0,30		
Cobb ₃₀ , Cobb ₆₀ , g/m ² , average for two sides, max.	sized paper	130*							
	unsized paper	Not applicable							
Moisture, %		7,5 ± 1,0							
Shade a		3,55+/-0,75 brown							
Shade b		15,0 +/-2,0 brown							
Reel diameter tolerance, mm		+10/-30							
Reel width tolerance, mm		+/-1							
Amount of mill joins		one per 10 reels							

* A specific value is set by agreement with the client

¹ Should be indicated in order specification

² Shade can vary, confirm the shade based on product samples